

# Technical Data Sheet



## Sunpol 4033C

### Water Reducible Alkyd

4033C is a chain-stopped water reducible alkyd based on dehydrated castor fatty acid (DCOFA). Formulated to provide fast drying tough films with fast cure response and humidity resistance. Provides low color with uncompromised dry times.

#### **Benefits:**

- ✓ Excellent Gloss
- ✓ Corrosion Resistance
- ✓ HAPs Free
- ✓ Color retention

#### **Applications:**

- Air Dry or Force Dry Primers & Enamels
- Industrial Coatings

#### **Typical Properties:**

---

Viscosity (Gardner)	Z5-Z7
Percent Solids (Weight)	69-71%
Reduced Viscosity in Butyl Glycol	Z3-Z5 @ 65% NVM
Color	6 Max
Acid Value	37-42
Density (lbs/gal)	8.7 +/- 0.1
Appearance	Clear
Solvent Type	Butyl Glycol

#### **Additional Information:**

---

Store in a dry location avoiding temperatures above 100 °F. Avoid contact with air/oxygen to ensure shelf life of at least one year. For all questions pertaining to this product (safety, quality, technical advice, etc.) please email [info@sunpol.com](mailto:info@sunpol.com)