

Technical Data Sheet



Sunpol 6060

Monomer Modified Alkyd Resin

6060 is an acrylic and vinyl toluene modified alkyd copolymer. Mixed modification allows for fast dry with improved stability and adhesion compared to classic VT alkyds.

Benefits:

- ✓ Rapid dry
- ✓ High Gloss
- ✓ High durability
- ✓ Strong adhesion

Applications:

- Marking Paints
- Aerosols

Typical Properties:

Viscosity (Gardner)	Z-Z2
Percent Solids (Weight)	59-61%
Reduced Viscosity (Gardner)	E-G @ 40% in VMP
Color	6 Max
Acid Value	10 Max
Density (lbs/gal)	7.50 +/- 0.1
Appearance	Clear/Slight Haze
Solvent Type	VM&P Spirits/Aromatic 100

Additional Information:

Store in a dry location avoiding temperatures above 100 °F. Avoid contact with air/oxygen to ensure shelf life of at least one year. For all questions pertaining to this product (safety, quality, technical advice, etc.) please email info@sunpol.com